

## IN THE SPECIFICATION

Please replace the two paragraphs beginning on Page 26 (no page number indicated) below the heading "Abstract" with the following single paragraph (i.e., two paragraphs have been combined into one):

-- An embodiment of a phase change TIM of this invention comprises a polyester matrix with melting temperature near or below operating temperature (typically less than about 130°C), thermally conductive filler with bulk thermal conductivity greater than about 50 W/mK, and optionally other additives. The polyester resin has improved thermo-oxidative stability compared to the polyolefin resins, thereby providing improved reliability performance during test. --